

EPOXY FLOORING SELF – LEVELING



DESCRIPTION

A solvent free, hard wearing, self–levelling epoxy floor coating applied at 3–6mm thickness
Resists most dilute acids, alkalis, petroleum products, aliphatic solvents, water and – .
.detergents.Available in a range of attractive colours

- High Gloss
- Easy to clean and resistant to bacteria –
- Bond strength: Breaks concrete –

WARNING : Good mixing is very important so that the quality does not differ from one site to another

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

No. of COMPONENTS	
COLOUR	See Colour Chart
MIXED DENSITY	kgs/ litre 1.7
VOC	5.1
COMPRESSIVE STRENGTH	N/mm ² 80<
FLEXURAL STRENGTH	N/mm ² 40 – 30
BOND STRENGTH	
(POT LIFE (500ml	minutes @ 25°C 30
TOUCH DRY	hours @ 25°C 8
CURE TIME: Foot Traffic	(to 16 Hrs @ 25°C 12
Chemical Spillage	to 7 Days 3
FULL CURE	days 7
SOLVENT CONTENT	Nil
VOLUME SOLIDS	100%
AVERAGE SPREAD RATE	Kit = 4m ² @ 3mm 1
FILM THICKNESS	3mm –8mm
SHELF LIFE	months 12
PACKAGING	5kg Base+2.5kg Activator+15kg Filler
YIELD	litres 12

3

